PROCESS FOR SYNTHESIZING POLYMERS BY CONTROLLED

FREE-RADICAL POLYMERIZATION WITH THE AID

OF HALOGENATED XANTHATES

The present invention relates to a novel

5 process for "controlled" or "living" free-radical

polymerization, giving access to block copolymers.

Block polymers are usually prepared by ionic

polymerization. A disadvantage of this type of

polymerization is that it permits the polymerization

10 only of certain types of non-polar monomers,

particularly styrene and butadiene, and that it

requires a particularly pure reaction environment, and

temperatures often lower than ambient, in order to

minimize side reactions, and the result is severe

15 operational constraints.

An advantage of free-radical polymerization

is that it is easy to implement without adhering to

excessive purity requirements, and at temperatures of

ambient or above. However, until recently there was no

20 free-radical polymerization process which could give

block polymers.

A novel process for free-radical

polymerization has now been developed: this is what is

known as "controlled" or "living" free-radical

25 polymerization. Controlled free-radical polymerization

proceeds by growth through propagation of

macroradicals. These macroradicals have a very short

lifetime and recombine irreversibly via coupling or dismutation. When the polymerization proceeds in the presence of a number of comonomers, the variation in the composition of the mixture is infinitely slow compared with the lifetime of the macroradical, and therefore the chains have a random sequence of monomer units, rather than a block-type sequence.

In recently developed techniques for controlled free-radical polymerization, the extremities of polymer chains can be reactivated as a radical by homolytic cleavage of a bond (for example C-O or C-halogen).

Controlled free-radical polymerization therefore has the following distinctive aspects:

1. the number of chains is fixed for the entire duration of the reaction,

2. all the chains grow at the same rate, resulting in:

* linear increase in molecular mass with conversion,

* a narrow distribution of masses,

3. the average molecular mass is controlled by the molar ratio monomer/chain precursor,

4. the possibility of preparing block copolymers.

The controlled character is all the more pronounced if the rate of reactivation of the free-

radical chains is very great compared with the rate of growth of the chains (propagation). There are cases where this does not always apply (i.e. the reactivation rate of the free-radical chains is greater than or

5 equal to the rate of propagation) and conditions 1 and 2 are not complied with, but it is nevertheless still possible to prepare block copolymers.

The publication WO 98/58974 describes a living free-radical polymerization process giving

10 access to block copolymers by a process without UV irradiation, by using xanthate compounds, i.e. compounds having the function:

$$\underset{-O}{\overset{S}{\underset{\diagup}{\parallel}}} C\text{-}S\,\text{---}$$

This free-radical polymerization allows

15 preparation of block polymers with the aid of any kind of monomer, without any UV source. The polymers obtained do not contain any metallic impurities detrimental to their use. They have chain-end functionalization and a low polydispersity index, lower

20 than 2, or even lower than 1.5.

It is an object of the present invention to propose a novel procedure for polymerization with the aid of new precursors of xanthate type.

Another object is to propose a polymerization

25 process which uses precursors of xanthate type and

during the course of which the number-average molar masses M_n of the resultant polymers are well controlled, i.e. close to the theoretical values $M_{n\ th}$, especially at the start of the polymerization reaction.

5   Another object is to propose a polymerization process which uses precursors of xanthate type to synthesize polymers and block copolymers whose index of polydispersity (M_w/M_n) is low, i.e. close to 1.

With this object in mind, the invention
10 provides a process for preparing polymers, characterized by bringing into contact:

- at least one ethylenically unsaturated monomer,
- at least one source of free radicals, and
- at least one compound (I) of general formula

15   (IA), (IB), or (IC):

$$\begin{array}{c} S \\ \| \\ C-S-R^1 \qquad \text{(IA)} \\ | \\ R^2-O \end{array}$$

$$R^2\!-\!\!\left(\!-O-\underset{\underset{S}{\|}}{C}-S-R^1\right)_p \qquad \text{(IB)}$$

$$R^{1'}\!-\!\!\left(\!-S-\underset{\underset{S}{\|}}{C}-O-R^2\right)_p \qquad \text{(IC)}$$

in which:

- R^2 and $R^{2'}$ represent:

    ○ an alkyl, acyl, aryl, alkene, or alkyne group (i), or

    ○ a carbocyclic system (ii), saturated or unsaturated, optionally aromatic, or

    ○ a heterocyclic system (iii), saturated or unsaturated,

these groups and cyclic systems (i), (ii), and (iii) being substituted by at least one fluorine atom, chlorine atom, and/or bromine atom,

- R^1 and $R^{1'}$ represent:

    ○ an alkyl, acyl, aryl, alkene, or alkyne group (i), optionally substituted, or

    ○ a carbocyclic system (ii), saturated or unsaturated, optionally substituted or aromatic, or

    ○ a heterocyclic system (iii), saturated or unsaturated, optionally substituted, where these groups and cyclic systems (i), (ii) and (iii) may be substituted by substituted phenyl groups, substituted aromatic groups, or: alkoxycarbonyl or aryloxycarbonyl (-COOR), carboxy (-COOH), acyloxy ($-O_2CR$), carbamoyl ($-CONR_2$), cyano (-CN), alkylcarbonyl, alkylarylcarbonyl, arylcarbonyl,

arylalkylcarbonyl, phthalimido, maleimido, succinimido, amidino, guanidimo, hydroxyl (-OH), amino ($-NR_2$), halogen, allyl, epoxy, alkoxy (-OR), S-alkyl, or S-aryl groups, groups

5   having hydrophilic or ionic character, for example the alkali metal salts of carboxylic acids, the alkali metal salts of a sulfonic acid, polyalkylene oxide chains (PEO, PPO), or cationic substituents (quaternary ammonium

10   salts),

R representing an alkyl or aryl group, or

• a polymer chain,

- **p** is between 2 and 10.

The process according to the invention

15 therefore consists in bringing into contact a source of free radicals, an ethylenically unsaturated monomer, and a compound (I) of formula (IA), (IB), or (IC).

This compound (I) bears a xanthate functionality. According to the essential

20 characteristic of the invention, the xanthate functionality bears a group R^2 or $R^{2'}$ which has to be substituted by at least one fluorine atom, chlorine atom, and/or bromine atom. R^2 and $R^{2'}$ are preferably substituted by at least one fluorine atom, and still

25 more preferably only by fluorine atoms.

According to one preferred version, R^2 represents a group of formula: $-CH_2R^{'5}$, in which $R^{'5}$

represents an alkyl group substituted by at least one fluorine atom, chlorine atom, and/or bromine atom. According to this embodiment, preferred groups R^2 are the following:

5
- CH_2CF_3,

- $CH_2CF_2CF_2CF_3$

- $CH_2CH_2C_6F_{13}$,

According to another preferred version, R^2 represents the group $CH(CF_3)_2$.

10
R^1 in the formulae (IA) and (IB) preferably represents:

- a group of formula $CR'^1R'^2R'^3$, in which:
  ○ R'^1, R'^2 and R'^3 represent the groups (i), (ii), or (iii) as defined above, or

15
  ○ $R'^1 = R'^2 = H$ and R'^3 is an aryl, alkene, or alkyne group,

- or a group of formula $-COR'^4$ in which R'^4 represents a group (i), (ii), or (iii) as defined above.

20
The most interesting results have been obtained for the compound (I) when R^1 is a group selected among:

- $CH(CH_3)(CO_2Et)$

- $CH(CH_3)(C_6H_5)$

25
- $CH(CO_2Et)_2$

- $C(CH_3)(CO_2Et)(S-C_6H_5)$

- $C(CH_3)_2(C_6H_5)$

$$H \quad O$$
$$| \quad ||$$
$$-C-C-Ph$$
$$|$$
$$O=\!\!\!\overset{N}{\diagup}\!\!\!=O$$

in which Et represents an ethyl group and Ph represents a phenyl group.

The groups R^1 and $R^{1'}$ may also represent a
5 polymer chain from a free-radical or ionic polymerization, or from a polycondensation. Preferred compounds of formula (IC) are those for which $R^{1'}$ is the group $- CH_2 -$ phenyl $- CH_2 -$ or the group $-$ $CHCH_3CO_2CH_2CH_2CO_2CHCH_3 -$.

10   In the preferred embodiment of the invention, the polymerization process uses a compound (I) of formula (IA). Preferred compounds of formula (IA) are ethyl a-(O-heptafluorobutylxanthyl)propionate ($R^1 = CHCH_3(CO_2Et)$, $R^2 = CH_2CF_2CF_2CF_3$),
15 ethyl a-(O-trifluoroethylxanthyl)propionate ($R^1 = CHCH_3(CO_2Et)$, $R^2 = CH_2CF_3$), and ethyl ethyl a-(O-tridecafluorooctanylxanthyl)propionate ($R^1 = CHCH_3(CO_2Et)$, $R^2 = CH_2CH_2C_6F_{13}$).

The compounds of formulae (IA), (IB), and
20 (IC) are easily accessible. They may particularly be obtained by reacting an alcohol R^2OH with carbon disulfide CS_2 (in the presence of hydrogen hydride, for example), giving the xanthate $R^2O(C=S)S^-Na^+$. This

xanthate is then reacted with an alkyl halide R^1X (X = halogen), giving the halogenated xanthate: $R^2O(C=S)-SR^1$.

According to the process of the invention,
5 the **free-radical source** is generally a free-radical polymerization initiator. However, for certain monomers, such as styrene, thermal initiation is sufficient to generate free radicals.

In the first case, the free-radical
10 polymerization initiator may be selected be selected among conventional initiators used in free-radical polymerization, for example one of the following initiators:

 - hydrogen peroxides, such as: tert-butyl
15 hydroperoxide, cumene hydroperoxide, tert-butylperoxy acetate, tert-butylperoxy benzoate, tert-butylperoxy octoate, tert-butylperoxy neodecanoate, tert-butylperoxy isobutarate, lauroyl peroxide, tert-amylperoxy pivalate, tert-butylperoxy pivalate, dicumyl
20 peroxide, benzoyl peroxide, potassium persulfate, ammonium persulfate,

 - azo compounds, such as:
2-2'-azobis(isobutyronitrile),
2,2'-azobis(2-butanenitrile), 4,4'-azobis(4-pentanoic
25 acid), 1,1'-azobis(cyclohexanecarbonitrile), 2-(tert-butylazo)-2-cyanopropane, 2,2'-azobis[2-methyl-N-(1,1)-bis(hydroxymethyl)-2-hydroxyethyl]propionamide,

2,2'-azobis(2-methyl-N-hydroxyethyl]propionamide,

2,2'-azobis(N,N'-dimethyleneisobutyramidine)

dichloride, 2,2'-azobis(2-amidinopropane) dichloride,

2,2'-azobis(N,N'-dimethyleneisobutyramide),

5 2,2'-azobis(2-methyl-N-[1,1-bis(hydroxymethyl)-2-

hydroxyethyl]propionamide), 2,2'-azobis(2-methyl-N-

[1,1-bis(hydroxymethyl)ethyl]propionamide),

2,2'-azobis[2-methyl-N-(2-hydroxyethyl)propionamide],

2,2'-azobis(isobutyramide) dihydrate,

10   - redox systems including combinations such

as:

          ∘ mixtures of hydrogen peroxide, alkyl

peroxide, peresters, percarbonates, and the like, and

any one of the salts of iron, titanous salts, zinc

15 formaldehyde-sulfoxylate, or sodium formaldehyde-

sulfoxylate, and reducing sugars,

          ∘ persulfates, perborate, or perchlorate of

alkali metals or of ammonium, combined with a bisulfite

of an alkali metal, such as sodium metabisulfite, and

20 reducing sugars,

          ∘ persulfate of an alkali metal combined with

an arylphosphinic acid, such as benzenephosphonic acid

and like compounds, and reducing sugars.

          The amount of initiator to be used is

25 generally calculated so that the amount of radicals

generated, as a ratio to the amount of compound (II),

is at most 20 mol%, preferably at most 5%.

According to the process of the invention, the **ethylenically unsaturated monomers** are more specifically selected among styrene or its derivatives, butadiene, chloroprene, (meth)acrylic esters, vinyl
5 esters and vinyl nitriles.

(Meth)acrylic esters denote the esters of acrylic acid and of methacrylic acid with hydrogenated or fluorinated C_1-C_{12} alcohols, preferably C_1-C_8 alcohols. Among compounds of this type mention may be
10 made of: methyl acrylate, ethyl acrylate, propyl acrylate, n-butyl acrylate, isobutyl acrylate, 2-ethylhexyl acrylate, tert-butyl acrylate, methyl methacrylate, ethyl methacrylate, n-butyl methacrylate, isobutyl methacrylate.

15 Vinyl nitriles include more particularly those having from 3 to 12 carbon atoms, such as, in particular, acrylonitrile and methacrylonitrile.

It should be noted that styrene may be partially or completely replaced by derivatives, such
20 as alpha-methylstyrene or vinyltoluene.

Particular other ethylenically unsaturated monomers which may be used, alone or as a mixture, or which may be copolymerized with the above monomers, are:

25 - vinyl esters of a carboxylic acid, e.g. vinyl acetate, vinyl Versatate®, vinyl propionate,
- vinyl halides,

- ethylenic unsaturated mono- and dicarboxylic acids, e.g. acrylic acid, methacrylic acid, itaconic acid, maleic acid, fumaric acid, and the monoalkyl esters of dicarboxylic acids of the type

5 mentioned with alkanols preferably having from 1 to 4 carbon atoms, and their N-substituted derivatives,

- amides of unsaturated carboxylic acids, e.g. acrylamide, methacrylamide, N-methylolacrylamide, or methacrylamide, N-alkylacrylamides.

10 - ethylenic monomers containing a sulfonic acid group and their alkali metal or ammonium salts, for example vinylsulfonic acid, vinylbenzenesulfonic acid, alpha-acrylamidomethylpropanesulfonic acid, 2-sulfoethylene methacrylate,

15 - amides of vinylamine, particularly vinylformamide or vinylacetamide,

- unsaturated ethylenic monomers containing a secondary, tertiary, or quaternary amino group, or a heterocyclic group containing nitrogen, for example

20 vinylpyridines, vinylimidazole, aminoalkyl (meth)acrylates, and aminoalkyl(meth)acrylamides, e.g. dimethylaminoethyl acrylate, dimethylaminoethyl methacrylate, di-tert-butylaminoethyl acrylate, di-tert-butylaminoethyl methacrylate,

25 dimethylaminomethylacrylamide, or -methacrylamide. It is equally possible to use zwitterionic monomers, for example sulfopropyl(dimethyl)aminopropyl acrylate.

To prepare polyvinylamines, the ethylenically unsaturated monomers used are preferably amides of vinylamine, for example vinylformamide or vinylacetamide. The polymer obtained is then

5   hydrolyzed, the pH being acidic or basic.

To prepare polyvinyl alcohols, the ethylenically unsaturated monomers used are preferably vinyl esters of carboxylic acid, for example vinyl acetate. The polymer obtained is then hydrolyzed, the

10   pH being acidic or basic.

The types and amounts of polymerizable monomers used according to the present invention vary as a function of the particular final application for which the polymer is destined. These variations are

15   well known and can readily be calculated by the skilled worker.

The polymerization may be carried out in bulk, in solution, or in emulsion. It is preferably implemented in emulsion.

20   The process is preferably implemented semi-continuously.

The temperature may vary between ambient temperature and 150°C, according to the nature of the monomers used.

25   The instantaneous polymer content as a ratio of the instantaneous amount of monomer and of polymer during the polymerization is generally between 50 and

99% by weight, preferably between 75 and 99%, still
more preferably between 90 and 99%. This content is
maintained in a known manner, via control of the
temperature, of the addition rate of the reactants,
5   and, optionally, of the polymerization initiator.

The process is generally implemented in the
absence of any UV source.

The process of the invention has the
advantage of allowing control of the number-average
10 molecular masses M_n of the polymers. Thus these masses
M_n are close to the theoretical values $M_{n\ th}$, where $M_{n\ th}$
is given by the following formula

$$M_{n\ th} = \frac{[M]_0}{[P]_0}\ \frac{X}{100}\ M_0$$

15 in which:

$[M]_0$ represents the initial molar
concentration of monomer

$[P]_0$ represents the initial concentration of
precursor compound

20   X represents the monomer conversion expressed
as a percentage

M_0 represents the molar mass of the monomer
(g/mol).

According to the present invention, the
25 control of Mn is particularly apparent at the start of
the polymerization.

In addition, the polymerization process according to the present invention leads to polymers with a low polydispersity index ($Ip = M_w/M_n$, where M_w : weight-average molecular mass), close to 1.

5   The invention therefore also provides **polymers** obtainable by the process consisting of bringing at least one ethylenically unsaturated monomer into contact with at least one source of free radicals and at least one compound of formula (IA), (IB), or 10 (IC).

The polymers generally have a polydispersity index of at most 2, preferably of at most 1.5.

The invention also provides a **process for preparing multiblock polymers**, in which the 15 implementation of the polymerization process described above is repeated at least once, using:

- compared with the preceding implementation, different monomers, and

- instead of the compound (I) of formula 20 (IA), (IB), or (IC), the polymer from the preceding implementation, known as a precursor polymer.

The complete process for synthesizing a block polymer according to the invention may therefore consist in:

25   (1) synthesizing a precursor polymer by bringing into contact an ethylenically unsaturated

monomer, a source of free radicals, and a compound of formula (IA), (IB), or (IC),

(2) using the precursor polymer obtained in step (1) to prepare a diblock polymer by bringing this

5 precursor polymer into contact with a new ethylenically unsaturated monomer and a source of free radicals.

This step (2) may be repeated as many times as desired with new monomers, to synthesize new blocks and obtain a multiblock polymer.

10 If the implementation is repeated once, a triblock polymer will be obtained, and if it is repeated a second time, a "quadriblock" polymer will be obtained, and so on. With each fresh implementation, therefore, the product obtained is a block polymer

15 having an additional polymer block.

To prepare multiblock polymers, therefore, the process consists in repeating the implementation of the preceding process a number of times on the block polymer coming from each preceding implementation, with

20 different monomers.

The compounds of formula (IB) and (IC) are particularly interesting because they allow a polymer chain to be grown at at least two active sites. With compounds such as these it is possible to economize on

25 polymerization steps to obtain a copolymer of n blocks. Thus, if the value of p is 2 in the formula (IB) or (IC), the first block is obtained by polymerizing a

monomer M1 in the presence of the compound of formula (IB) or (IC). This first block may then grow at each of its extremities via polymerization of a second monomer M2. A triblock copolymer is obtained, and this triblock

5 polymer itself can grow at each of its extremities via polymerization of a third monomer M3. Thus, a "pentablock" copolymer is obtained in only three steps. If p is greater than 2, the process can give homopolymers or block copolymers whose structure is

10 "multi-branched" or hyperbranched.

According to this process for preparing multiblock polymers, if it is desired that the block polymers obtained are homogeneous and do not have a composition gradient, and if all of the successive

15 polymerizations are carried out in the same reactor, it is essential that all the monomers used in one step are consumed before the polymerization of the next step starts, e.g. before the new monomers are introduced.

As for the process for polymerizing a

20 monoblock polymer, this process for polymerizing block polymers has the advantage of leading to block polymers having a low polydispersity index. It also allows control of the molecular mass of block polymers.

The invention therefore provides block

25 polymers obtainable by the preceding process.

These block polymers generally have a polydispersity index of at most 2, preferably of at most 1.5.

The invention particularly provides block polymers which have at least two polymer blocks selected among the following partners:

- polystyrene/polymethyl acrylate
- polystyrene/polyethyl acrylate,
- polystyrene/polytert-butyl acrylate,
- polyethyl acrylate/polyvinyl acetate,
- polybutyl acrylate/polyvinyl acetate
- polytert-butyl acrylate/polyvinyl acetate.

When use is made of compounds of formula (IA), the block polymers obtained have a structure of the type:

$$\underset{R^2-O}{\overset{S}{\diagdown}}C-S\left[\begin{array}{c}Y\\|\\C-(CW=CW')_a-CH_2\\|\\Y'\end{array}\right]_m\left[\begin{array}{c}X\\|\\C-(CV=CV')_b-CH_2\\|\\X'\end{array}\right]_n R' \quad \text{(IIIA)}$$

in which:

- R^2, R^1 are as defined above,

- V, V', W and W' are identical or different and represent: H, an alkyl group, or a halogen,

- X, X', Y, and Y' are identical or different and represent H, a halogen, or an R^3, OR^3, O_2COR^3, NHCOH, OH, NH_2, NHR^3, $N(R^3)_2$, $(R^3)_2N^+O^-$,

$NHCOR^3$, CO_2H, CO_2R^3, CN, $CONH_2$, $CONHR^3$ or $CONR^3_2$ group, in which R^3 is selected among alkyl, aryl, aralkyl, alkaryl, alkene, or organosilyl groups, optionally perfluorinated, and optinally substituted by one or more carboxy, epoxy, hydroxyl, alkoxy, amino, halogen, or sulfonic groups,

- a and b are identical or different and have values 0 or 1,

- m and n are identical or different and are greater than or equal to 1, and if one of these is greater than 1, the repeat units are identical or different.

These block polymers are the result of bringing into contact:

- an ethylenically unsaturated monomer of formula: CYY' (= $CW - CW'$)$_b$ = CH_2,

- a precursor polymer of general formula (IIA):

$$\underset{R^2-O}{\overset{S}{\diagdown}}C-S\left[\underset{X'}{\overset{X}{\underset{|}{\overset{|}{C}}}}-(CV=CV')_b-CH_2\right]_n R^1 \quad \text{(IIA)}$$

- a source of free radicals.

The polymer (IIA) is the result of bringing into contact an ethylenically unsaturated monomer of formula: CXX' (= $CV - CV'$)$_a$ = CH_2, a compound (I) of general formula (IA) and a source of free radicals.

In the formula (IIA), n is preferably greater than or equal to 6.

Particularly preferred compounds (IIA) are homopolymers of styrene (Y' = H, Y = C_6H_5, b = 0), of methyl acrylate (Y' = H, Y = COOMe, b = 0), of ethyl acrylate (Y' = H, Y = COOEt, b = 0), of butyl acrylate (Y' = H, Y = COOBu, b = 0), of tert-butyl acrylate (Y' = H, Y = COOtBu, b = 0), of vinyl acetate (Y' = H, Y = OCOMe, b = 0), of acrylic acid (Y' = H, Y = COOH, b = 0), and for which:

- R^1 = $CHCH_3(CO_2Et)$, $CH(CO_2Et)_2$, or $C(CH_3)_2(C_6H_5)$, and

- R^2 = $-CH_2CF_3$, $-CH_2CF_2CF_2CF_3$, or $CH_2CH_2C_6F_{13}$.

The examples below illustrate the invention but do not restrict its scope.

Figure 1 gives curves for M_n and M_w/M_n as a function of the conversion rate of the ethyl acrylate monomer when using a xanthate according to the invention and of a xanthate according to the prior art.

Figure 2 gives curves for M_n and M_w/M_n as a function of the conversion rate of the styrene monomer when using a xanthate according to the invention and of a xanthate according to the prior art.

EXAMPLES

**EXAMPLES 1 - SYNTHESES OF PRECURSORS OF FORMULA (IA)
(xanthates)**

Example 1.1 - Synthesis of the precursor ethyl a-(O-
5 **heptafluorobutylxanthyl)propionate (A)**

       1 g (5 mmol) of heptafluorobutanol is
dissolved in 10 ml of DMF (N,N-dimethylformamide) in a
glass flask. 0.6 ml (10 mmol) of CS_2 is added. The
solution is cooled to 0°C, and then 0.24 g (5 mmol) of
10 NaH is added. After 1 hour of stirring at 0°C, 0.6 ml
(4.5 mmol) of ethyl 2-bromopropionate is added. The
solution is stirred for 1 hour at 0°C, then 2 hours at
ambient temperature, before being diluted with ethyl
ether. It is then washed with water, and then with
15 brine. The organic phase is concentrated in vacuo, and
then the crude product is purified through a column
(9/1: heptane/ethyl acetate). 1.5 g (88% yield) of
product A are isolated.

20 **Example 1.2 - Synthesis of the precursor ethyl a-(O-**
trifluoroethylxanthyl)propionate (B)

       2 g (20 mmol) of trifluoroethanol are
dissolved in 40 ml of DMF in a glass flask. 2.4 ml
(40 mmol) of CS_2 are added. The solution is cooled to
25 0°C, and then 0.96 g (20 mmol) of NaH is added. After
1 hour of stirring at 0°C, 2.34 ml (18 mmol) of ethyl
2-bromopropionate is added. The solution is stirred for

1 hour at 0°C, then two hours at ambient temperature, before being diluted with ethyl ether. It is then washed with water, and then with brine. The organic phase is concentrated in vacuo, and then the crude

5   product is purified through a column (9/1: heptane/ethyl acetate). 3.4 g (69% yield) of xanthate B are isolated.

Example 1.3 - Synthesis of the precursor ethyl a-(O-tridecafluorooctanylxanthyl)propionate (C)

10   1.1 ml (5 mmol) of tridecafluorooctanol are dissolved in 10 ml of DMF in a glass flask. 0.6 ml (10 mmol) of CS_2 is added. The solution is cooled to 0°C, and then 0.24 g (5 mmol) of NaH is added. After 1 hour of stirring at 0°C, 0.6 ml (4.5 mmol) of ethyl

15   2-bromopropionate is added. The solution is stirred for 1 hour at 0°C, then 2 hours at ambient temperature, before being diluted with ethyl ether. It is then washed with water, and then with brine. The organic phase is concentrated in vacuo, and then the crude

20   product is purified through a column (9/1: heptane/ethyl acetate). 2.27 g (93% yield) of xanthate C are isolated.

EXAMPLES 2 - SYNTHESES OF POLYMERS (homopolymers)

25   These examples show that the free-radical polymerization is controlled due to the use of the xanthates of the invention.

In the examples below the polymers are analyzed by GPC with THF as eluting solvent; M_n is expressed in polystyrene equivalents (g/mol).

Example 2.1 – Homopolymerization of ethyl acrylate in
5 **the presence of B.**

- 0.02 mmol of azobisisobutyronitrile (AIBN) (3.38 mg),

- 54.9 mmol of ethyl acrylate (5.5 g)

- 0.69 mmol of xanthate B (0.19 g)

10 - 5.97 cm^3 of toluene (5.17 g).

are introduced into a glass flask.

The solution obtained is divided into eight fractions distributed over the same number of Carius tubes. The tubes are connected to a vacuum line, and

15 immersed in liquid nitrogen, and then the contents of each tube are subjected to three cycles of "freezing/vacuum/back to ambient" to degas the tubes. They are then vacuum-sealed. After return to ambient, they are immersed in an oil bath preheated to 80°C.

20 They are taken from the oil bath in sequence at regular intervals of time (t) and immersed in liquid nitrogen so that the polymerization is ended and the tubes can be analyzed.

The polymer is recovered by opening the tube

25 and then evaporating traces of residual monomer.

Both of the following are tested:

- precursor conversion by GPC (UV detection), and

- monomer conversion by gravimetric analysis.

The results obtained are reported in table 1

5 and figure 1.

Table 1

Test	t (min)	Monomer conversion (%)	Precursor conversion (%)	M_n	M_w/M_n
1	5	<1			
2	15	4.2	36.3	2 790	1.98
3	20	11	72.6	2 940	2.00
4	25	25.7	73.4	3 600	1.81
5	35	46.4	92	5 115	1.58
6	53	84.1	>99	6 756	1.52
7	80	89.9	>99	7 716	1.43
8	140	91.8	>99	7 946	1.42

Figure 1 compares the results obtained with the xanthate B and those obtained with ethyl

10 a-(O-ethylxanthyl)propionate (R^2 = ethyl), under the same conditions of initial molar concentrations and temperature.

The value of M_n is found to be better controlled with xanthate B: the value approaches the

15 theoretical value ($M_{n\ th}$) from the start of the polymerization, unlike in the case of the

polymerization with the xanthate of the prior art (ethyl a-(O-ethylxanthyl)propionate).

In addition, the value of M_w/M_n tends rapidly toward 1 in the case of xanthate B, whereas this value remains stable at more than 1.6 for the xanthate of the prior art (ethyl a-(O-ethylxanthyl)propionate).

Example 2.2 - Homopolymerization of ethyl acrylate in the presence of C.

1.08 ml are taken from a solution composed of 3.9 mg of AIBN and 7.5 ml of ethyl acrylate. This fraction is added to 68.1 mg (0.126 mmol) of xanthate C in a Carius tube. The tube is degassed, then vacuum-sealed. The reaction takes 21 h at 80°C.

The monomer conversion is 95%.

The xanthate conversion is 100%.

The value of M_n is 9 400 g/mol

The value of M_w/M_n is 1.48.

At a high conversion rate, the value of the polymerization index is found to be low, and close to 1.

Example 2.3 - Homopolymerization of ethyl acrylate in the presence of A.

- 0.01 mmol of AIBN (1.69 mg),

- 31.9 mmol of ethyl acrylate (3.192 g)

- 0.4 mmol of xanthate A (0.15 g)

- 3.47 cm^3 of toluene (3 g).

are introduced into a glass flask.

Five tubes are prepared and vacuum-sealed in a manner similar to that used in example 2.1. The analyses are carried out in the same manner.

The results are reported in table 2.

Table 2

Test	t (min)	Monomer conversion (%)	Precursor conversion (%)	M_n	M_w/M_n
1	15	<1			
2	25	11.3	42.6	3 603	1.76
3	35	24.7	70.4	4 590	1.62
4	45	45.3	93.9	5 934	1.55
5	90	81.8	>99	8 380	1.41

At high conversion, the values of the polydispersity index is found to be close to 1.4.

Example 2.4. – Homopolymerization of styrene in the presence of B.

- 3.016 g (3.32 ml, 28.9 mmol) of styrene

- 0.1 g (0.36 mmol) of xanthate B

- 3.32 ml of toluene.

are introduced into a glass flask.

The mixture obtained is separated into 5 fractions distributed among the same number of Carius tubes. These are degassed, then vacuum-sealed, and then placed in an oven kept at 110°C. At regular intervals

of time the tubes are removed, cooled, and then opened.
The results obtained are given in table 3 and figure 2.

Table 3

Test	T (hours)	Monomer conversion (%)	M_n	M_w/M_n
1	2	7.8	2 660	1.93
2	5.33	16	2 940	1.89
3	16.25	28	3 520	1.77
4	25.5	41.1	3 830	1.76
5	89.5	65.8	5 600	1.57

5   Figure 2 compares the results obtained with
xanthate B and those obtained with ethyl
a-(O-ethylxanthyl)propionate (R^2 = ethyl), under the
same conditions of initial molar concentrations and
temperature.

10   The value of M_n is found to be better
controlled with xanthate B: the value approaches the
theoretical value ($M_{n\ th}$) from the start of the
polymerization, unlike in the case of the
polymerization with the xanthate of the prior art
15 (ethyl a-(O-ethylxanthyl)propionate).

In addition, the value of M_w/M_n tends rapidly
toward 1 in the case of xanthate B, whereas this value
remains stable at about 2 for the xanthate of the prior
art (ethyl a-(O-ethylxanthyl)propionate).

20

Example 2.5 - Homopolymerization of vinyl acetate in the presence of B.

      - 4.73 g (55 mmol) of vinyl acetate

      - 0.19 g (0.69 mmol) of xanthate B

5   - 3.38 mg (0.02 mmol) of AIBN.

are introduced into a glass tube.

      The tube is degassed, then vacuum-sealed. After 8 h 20 at 60°C, the tube is opened and the polymer is analyzed:

10   - monomer conversion: 11.3%

      - M_n = 740 g/mol

      - M_w/M_n = 1.19.

      Under the same conditions of temperature and of initial concentration, it is found that the xanthate

15 of the prior art (ethyl a-(O-ethylxanthyl)propionate) allows M_n to be controlled (< 1 000 g/mol) to approximately 10% monomer conversion, while the value of M_w/M_n remains in the vicinity of 1.5.

20 ## Example 2.6 - Homopolymerization of styrene in the presence of B.

      - 0.81 g (0.9 ml, 7.8 mmol) of styrene

      - 27.7 mg (0.1 mmol) of xanthate B

      - 0.93 ml of toluene.

25 are introduced into a glass tube.

The tube is degassed, then vacuum-sealed. After 114 hours at 120°C, the tube is opened and the polymer is characterized. The results are as follows:

- monomer conversion: 84.4%

- M_n = 7 500 g/mol

- M_w/M_n = 1.57

At high conversion the value of the polymerization index is found to be low and close to 1.

Example 2.7 - Homopolymerization of ethyl acrylate in the presence of B.

- 1.61 g (1.75 ml, 16.1 mmol) of ethyl acrylate

- 52.6 mg (0.19 mmol) of xanthate B

- 1.84 ml of toluene.

are introduced into a glass tube.

The tube is degassed, then vacuum-sealed. After 20 hours at 80°C, the tube is opened and the polymer is characterized. The results are as follows:

- monomer conversion: 88.1%

- M_n = 8 200 g/mol

- M_w/M_n = 1.69

At high conversion the value of the polymerization index is found to be low and close to 1.

EXAMPLES 3 - SYNTHESES OF BLOCK POLYMERS

Example 3.1 - Synthesis of a polystyrene-b-ethyl polyacrylate diblock copolymer

- 0.25 g of the polystyrene described in example 2.6

- 0.3 g (3 mmol) of ethyl acrylate

- 0.15 mg (9.10^{-7} mol) of AIBN

- 0.57 ml of toluene

are introduced into a glass tube.

The tube is degassed, then vacuum-sealed. After 20 h at 120°C, the tube is opened and the copolymer is characterized. The results are as follows:

- monomer conversion: 40.1%

- M_n = 12 400 g/mol

- M_w/M_n = 1.45.

Under the same conditions of temperature and of initial concentration, it is found that the xanthate of the prior art (ethyl a-(O-ethylxanthyl)propionate) leads to a diblock copolymer having a polydispersity index of 1.8.

Example 3.2 - Synthesis of a polystyrene-b-butyl polyacrylate diblock copolymer

- 0.175 g of the polystyrene described in example 2.6

- 0.27 g (2.12 mmol) of butyl acrylate

- 0.15 mg (9.10^{-7} mol) of AIBN

- 0.57 ml of toluene

are introduced into a glass tube.

The tube is degassed, then vacuum-sealed.
After 20 h at 120°C, the tube is opened and the
5   copolymer is characterized. The results are as follows:

- monomer conversion: 42.4%

- M_n = 12 100 g/mol

- M_w/M_n = 1.66.

10 **Example 3.3 – Synthesis of a polyethyl acrylate-b-
polyvinyl acetate diblock copolymer**

- 0.2 g of the polyethyl acrylate described
in example 2.7

- 0.2 g (2.3 mmol) of vinyl acetate

15 - 0.44 mg ($3.6.10^{-6}$ mol) of AIBN

- 0.32 g of methyl ethyl ketone

are introduced into a glass tube.

The tube is degassed, then vacuum-sealed.
After 20 h at 80°C, the tube is opened and the polymer
20 is characterized. The results are as follows:

- monomer conversion: 71%

- M_n = 13 300 g/mol

- M_w/M_n = 1.66.

Example 3.4 - Synthesis of a polystyrene-b-polyvinyl acetate diblock copolymer

- 0.2 g of the polystyrene described in example 2.6

5

- 0.2 g (2.3 mmol) of vinyl acetate

- 0.44 mg ($3.6.10^{-6}$ mol) of AIBN

- 0.32 ml of toluene

are introduced into a glass tube.

The tube is degassed, then vacuum-sealed. After 20 h at 80°C, the tube is opened and the polymer is characterized. The results are as follows:

- monomer conversion: 74%

- $M_n = 12\ 800$ g/mol

- $M_w/M_n = 1.61$.